



Domolen 1100 L

Domolen 1100L is a homopolymer with a conventional molecular weight distribution and is formulated with a general-purpose additive package. Domolen 1100L is designed for injection moulding applications, closures and houseware.

Food Contact Applications: This grade is in compliance with most regulations regarding food contact applications (EU, FDA). Specific information is available upon request.

Properties (Typical values)

Properties	Unit	Test method	Value	
<u>Melt flow rate</u>				
MFR 230 / 2. 16	g/10 min	ISO 1133	6	
<u>Technical properties</u>				
Tensile modulus of elasticity (v = 1mm/min)	MPa	ISO 527-2	1500	
Tensile yield stress (v = 50mm/min)	MPa	ISO 527-2	34	
Tensile yield strain (v = 50mm/min)	%	ISO 527-2	9	
Tensile strain at break (v = 50mm/min)	%	ISO 527-2	>50	
Tensile creep modulus (1000h, elongation ≤ 0.5%)	MPa	ISO 899-1	380	
Shear modulus	MPa	ISO 6721-2	750	
Charpy impact strength notched	+ 23°C	kJ/m ²	ISO 179 / 1eA	3.5
	- 30°C	kJ/m ²	ISO 179 / 1eA	1.5
Charpy impact strength unnotched	+ 23°C	kJ/m ²	ISO 179 / 1eU	140
	- 30°C	kJ/m ²	ISO 179 / 1eU	16
Izod impact strength notched	+ 23°C	kJ/m ²	ISO 180 / 1A	3.5
	- 30°C	kJ/m ²	ISO 180 / 1A	1.3
Ball indentation hardness (H 358/30)	MPa	ISO 2039-1	74	
<u>Thermal properties</u>				
Melting point, DSC	°C	ISO 3146	163	
Heat deflection temperature:				
- HDT / A (1.8 MPa)	°C	ISO 75-2	55	
- HDT / B (0.45 MPa)	°C	ISO 75-2	85	
Vicat softening temperature:				
- VST / A (10N)	°C	ISO 306	154	
- VST / B (50N)	°C	ISO 306	90	
<u>Other properties</u>				
Haze (injection moulded disk, 1 mm)	%	ASTM D1003	60	
Density	g/cm ³	ISO 1183	0.91	
<u>Applications</u>				
Closures, housewares, general injection moulding				

Last updated: 01-06-2010

For further information please contact: polypropylene@domo.org

DOMO cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. DOMO accepts no responsibility for results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, DOMO sells the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. The property values quoted are typical of European produced grades only and do not constitute a specification. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.